



## NOTES:

- 1. This apparatus is to be used for the test described in Clause 2601.4(iii).
- 2. Dimension A is 10mm for grouts appropriate to plinth height 10-25mm and 20mm for grouts appropriate to plinth height 20-50mm.
- Grout is to be mixed and poured using the Contractor's proposed site method until it reaches the underside of the top plate and has risen up the containing walls to a depth of at least 10mm.
- Plates are to be horizontal during pouring and curing, and are not to be moved once pouring has commenced until dismantling.
- 5. All dimensions are in mm.

HIGHWAY CONSTRUCTION DETAILS

MISCELLANEOUS

А	DEC 9
Issue	Date

BEDDING MORTAR TEST APPARATUS FOR FLOW BETWEEN GLASS PLATES Drawing No.

K2





